

## Tubo per mandata carburanti ed olio

**Applicazione:** tubo cord utilizzato per passaggio di prodotti petroliferi con contenuto aromatico fino al 30%. Disponibile a 10 e 15-18 bar.

**Temperature:** da -20°C a +70°C.

### COSTRUZIONE

**Sottostrato:** nero, liscio, in gomma NBR.

**Rinforzi:** tessuti sintetici ad alta resistenza e trecce rame antistatiche.

**Copertura:** nera, liscia (ad impressione tela), in gomma CR resistente agli agenti atmosferici e all'olio.

**Marcatura:** transfer ad elica di colore rosso

Disponibile inoltre:

- ① Australia D.M. 48 (in accordo al decreto ministeriale 48).
- ② Australia EN 1761 (in accordo alla normativa).
- ③ Australia Reel hose per arrotolatori (per aromatici fino al 50%).
- ④ Australia Super per aromatici fino al 50%.
- ⑤ Australia Super Conduttivo con mescola conduttiva in sottostrato (per aromatici fino al 50%).

## Fuel & oil delivery hose

**Application:** softwall hose used for the delivery and transfer of a wide range of petroleum products with aromatic content up to 30%. Available at 10, 15-18 bar.

**Temperature range:** -20°C (-4°F) to +70°C (+158°C).

### CONSTRUCTION

**Tube:** black, smooth, NBR rubber compound.

**Reinforcement:** high strength synthetic cord plus antistatic copper wires.


**Cover:** black, smooth (wrapped finish) CR rubber compounded for an excellent resistance to weathering and oil.

**Branding:** continuous spiral red brand

Also available:


- ① Australia D.M. 48 (according to legal ordinance, 48)
- ② Australia EN 1761 (according to EN 1761 specification)
- ③ Australia Reel hose (50% aromatic content).
- ④ Australia Super (50% aromatic content).
- ⑤ Australia Super Conductive with electrical conductive rubber compound tube (50% aromatic content).





CODICE <i>CODE</i>	diametro interno		diametro esterno		pressione di esercizio		pressione di scoppio (teorica)		peso (nominale)	
	<i>inside diameter</i>		<i>outside diameter</i>		<i>working pressure</i>		<i>burst pressure (theoretical)</i>		<i>weight (nominal)</i>	
	mm	inch	mm	inch	bar	psi	bar	psi	kg/m	lbs/ft
<b>10 bar - 30% Ar.</b> 1008315	10	25/64	17	43/64	10	150	30	450	0.20	0.14
1349287	13	1/2	20	25/32	10	150	30	450	0.25	0.17
1008374	15	19/32	23	29/32	10	150	30	450	0.31	0.21
1344269	19	3/4	27	1-1/16	10	150	30	450	0.39	0.26
1301802	19	3/4	32	1-1/4	10	150	30	450	0.69	0.46
1008463	25	1	35	1-3/8	10	150	30	450	0.66	0.44
1322435	25	1	36	1-27/64	10	150	30	450	0.74	0.50
1357930	32	1-1/4	42	1-21/32	10	150	30	450	0.82	0.55
1295500	32	1-1/4	44.5	1-11/16	10	150	30	450	1.04	0.69
1297236	35	1-3/8	45	1-49/64	10	150	30	450	0.79	0.53
1357956	38	1-1/2	47	1-27/32	10	150	30	450	0.77	0.52
1247808	38	1-1/2	48	1-57/64	10	150	30	450	0.86	0.57
1296086	38	1-1/2	50	1-31/32	10	150	30	450	1.12	0.75
1008641	40	1-37/64	50	1-31/32	10	150	30	450	0.90	0.60
1363360	45	1-49/64	55	2-11/64	10	150	30	450	1.01	0.68
1370154	51	2	61	2-13/32	10	150	30	450	1.12	0.75
1296060	51	2	63	2-1/2	10	150	30	450	1.42	0.96
1304232	51	2	65	2-9/16	10	150	30	450	1.70	1.15
1322443	60	2-3/8	73	2-7/8	10	150	30	450	1.82	1.22
1295497	63.5	2-1/2	74	2-29/32	10	150	30	450	1.46	0.98
1282832	76	3	89	3-1/2	10	150	30	450	2.14	1.44
1304240	76	3	91.5	3-5/8	10	150	30	450	2.62	1.76
1363344	90	3-35/64	105	4-9/64	10	150	30	450	2.87	1.93
1358006	102	4	115.5	4-9/16	10	150	30	450	2.97	2.00
<b>15-18 bar - 30% Ar.</b> 1009257	8	5/16	17	43/64	18	270	54	810	0.28	0.18
1392417	10	25/64	19	3/4	18	270	54	810	0.27	0.18
1278070	16	5/8	26	1-1/32	15	225	45	675	0.47	0.32
1214683	19	3/4	31	1-7/32	18	300	54	900	0.64	0.43
1278061	25	1	35	1-3/8	15	225	45	675	0.60	0.40
1277626	30	1/2	40	7/8	15	225	45	675	0.72	0.48
1306901	32	1-1/4	44	1-47/64	18	270	54	810	0.96	0.64
1277642	38	1-1/2	48.5	1-59/64	15	225	45	675	0.94	0.63
1301489	38	1-1/2	51	2	15	225	45	675	1.23	0.82
1295780	38	1-1/2	52.5	2-3/32	18	270	54	810	1.31	0.88
1319698	51	2	63.5	2-1/2	15	225	45	675	1.37	0.92
1301462	63.5	2-1/2	76.5	3	15	225	45	675	1.84	1.24
1387782	76	2-1/2	91	3	18	270	54	810	2.33	1.57

	CODICE <i>CODE</i>	diametro interno		diametro esterno		pressione di esercizio		pressione di scoppio (teorica)		peso (nominale)	
		<i>inside diameter</i>		<i>outside diameter</i>		<i>working pressure</i>		<i>burst pressure (theoretical)</i>		<i>weight (nominal)</i>	
		mm	inch	mm	inch	bar	psi	bar	psi	kg/m	lbs/ft
① D.M. 48 15 bar	<b>1394444</b>	<b>6</b>	1/4	<b>13</b>	1/2	<b>15</b>	225	<b>45</b>	675	<b>0.13</b>	0.09
	<b>1394436</b>	<b>8</b>	5/16	<b>16</b>	5/8	<b>15</b>	225	<b>45</b>	675	<b>0.19</b>	0.13
	<b>1394428</b>	<b>9</b>	23/64	<b>17</b>	43/64	<b>15</b>	225	<b>45</b>	675	<b>0.21</b>	0.14
	<b>1394410</b>	<b>10</b>	25/64	<b>18</b>	23/32	<b>15</b>	225	<b>45</b>	675	<b>0.23</b>	0.15
	<b>1394401</b>	<b>12</b>	15/32	<b>20</b>	25/32	<b>15</b>	225	<b>45</b>	675	<b>0.26</b>	0.17
② EN 1761	<b>1404377</b>	<b>32</b>	1-1/4	<b>44</b>	1-47/64	<b>10</b>	150	<b>40</b>	600	<b>0.90</b>	0.61
	<b>1404369</b>	<b>35</b>	1-3/8	<b>48.5</b>	1-57/64	<b>10</b>	150	<b>40</b>	600	<b>1.05</b>	0.70
	<b>1404385</b>	<b>38</b>	1-1/2	<b>51.5</b>	2	<b>10</b>	150	<b>40</b>	600	<b>1.12</b>	0.75
③ REEL	<b>1382713</b>	<b>40</b>	1-37/64	<b>54</b>	2-1/8	<b>10</b>	150	<b>30</b>	450	<b>1.33</b>	0.89
	<b>1382705</b>	<b>45</b>	1-49/64	<b>59</b>	2-21/64	<b>10</b>	150	<b>30</b>	450	<b>1.47</b>	0.99
	<b>1378740</b>	<b>50</b>	1-31/32	<b>64</b>	2-17/32	<b>10</b>	150	<b>30</b>	450	<b>1.59</b>	1.07
	<b>1380605</b>	<b>60</b>	2-3/8	<b>74</b>	2-29/32	<b>10</b>	150	<b>30</b>	450	<b>1.87</b>	1.26



CODICE CODE	diametro interno inside diameter		diametro esterno outside diameter		pressione di esercizio working pressure		pressione di scoppio (teorica) burst pressure (theoretical)		peso (nominale) weight (nominal)		
	mm	inch	mm	inch	bar	psi	bar	psi	kg/m	lbs/ft	
④ SUPER 15-18-20 bar	1333461	13	1/2	21	53/64	20	300	60	900	0.28	0.19
	1394762	19	3/4	27	1-1/16	15	225	45	675	0.39	0.26
	1395823	25	1	35	1-3/8	18	270	54	810	0.58	0.39
	1393880	32	1-1/4	43	1-11/16	18	270	54	810	0.81	0.55
	1384120	35	1-3/8	49	1-59/64	20	300	60	900	1.12	0.76
	1393871	38	1-1/2	50.5	2	18	270	54	810	1.05	0.70
	1364251	38	1-1/2	52	2-3/64	15	225	45	675	1.31	0.88
	1337424	40	1-37/64	53	2-3/32	15	225	45	675	1.16	0.78
	1341073	42	1-21/32	56	2-13/14	15	225	45	675	1.24	0.83
	1329421	45	1-49/64	59	2-21/64	15	225	45	675	1.31	0.88
	1393863	51	2	63	2-1/2	18	270	54	810	1.32	0.89
	1298089	51	2	67	2-41/64	15	225	45	675	1.79	1.21
	1393553	76	3	91	3-19/32	16	240	48	720	2.47	1.66
	1388487	102	4	118	4-41/64	15	225	45	675	3.42	2.30
⑤ SUPER COND.	1377477	20	25/32	30	1-3/16	10	150	30	450	0.51	0.34
	1303864	23	29/32	30	1-3/16	10	150	30	450	0.33	0.22
	1375270	25	1	35	1-3/8	10	150	30	450	0.63	0.42
	1371886	28	1-7/64	40	1-37/64	10	150	30	450	0.85	0.57
	1385976	51	2	64	2-17/32	10	150	30	450	1.50	1.01

max lunghezza prodotta max manufactured length		fino al D.I. up to I.D.	
m	ft	mm	inch
120	400	102	4

Oil